








Treviscreen



Treviscreen

Gewebe	DIN 60 001		100% PES Trevira CS
Flächengewicht (g/m ²)	DIN EN 12127		315
Gewebedicke (mm)	DIN ISO 2286-3		0.50
Stoffbreite (cm)			320
Schwerentflammbarkeit			B1 (DIN 4102)
Pflegehinweise			

Solar und Optische Kennzahlen (DIN EN 410) Alle Werte sind Nennwerte mit einer Toleranz von +/- 5%

Farbe	400	410	402	401	463	429	411
T_v	32	34	30	24	13	6	2
R_v	62	63	64	56	40	24	6
A_v	6	3	6	20	47	70	92
T_s	35	34	32	29	24	21	19
R_s	60	58	59	55	48	42	33
A_s	5	8	9	16	28	37	48
UV	24	12	10	6	4	3	2
g_{tot}	0.41	0.42	0.41	0.42	0.45	0.48	0.52
F_c	0.57	0.58	0.57	0.59	0.63	0.67	0.72

T_v Lichttransmissionsgrad (%)

R_v Lichtreflexionsgrad (%)

A_v Lichtabsorptionsgrad (%)

UV UV-Transmissionsgrad (%)

F_c Abminderungsfaktor (pf EN 14501 2005)

T_s Strahlungstransmissionsgrad (%)

R_s Strahlungsreflexionsgrad (%)

A_s Strahlungsabsorptionsgrad (%)

g_{tot} Gesamt g-Wert (Glas g-Wert: 0,72; 1,6 W/m² K) DIN EN 13363-1



400



410



402




401



463



429



411